

Epifanes Woodfinish Gloss

One-component yacht varnish alternative + extra UV filter



PRODUCT DESCRIPTION

Extreme high gloss, unique flow characteristics and high build capacity. This varnish alternative is very well suited for tropical woods with a high oil content i.e. teak and iroco providing great bonding. The UV filter protects the wood for discolouration. Its flexibility prevents cracking on working wood. Due to special components this oil based varnish has breathing characteristics, this preventing dark spots underneath the varnish.

Field of use: New work on bare solid wood (teak, iroco) and plywood both for inside and outside above the waterline. Maintenance of intact existing (one- and two-component) varnishes regardless of brand. Not suited for direct use on epoxy resin.

PRODUCT INFORMATION

Type	Oxidative drying
Base	Phenolic resin / Alkyd resin / Tung Oil, inert regulating components
Gloss	High gloss
Colour	Light milky colour after steering, but dries up completely clear
Density at 20°C.	0,940 g/cm ³
Viscosity	55 seconds ISO-cup 6 mm
Solids Contents	55 ± 2 vol. %
VOC-level	367 g/l
Packing	500ml. - 1000ml.
Shelf life	3 years in original closed container stored in a location between 5 - 30°C
Rec. filmthickness	60 - 70 µm wet = 30 - 35 µm dry
Thinner brush	Epifanes Brushthinner for Paint & Varnish or a good quality white spirit
Thinner spray	Epifanes Spraythinner for Paint & Varnish or denaturated alcohol
Thinning in general	Thinning ratio depends on product temperature and working area. Avoid overthinning. For thinning ratios, see the Epifanes varnish system.

Drying times	10°C.	15°C.	20°C.	25°C.
Dust dry	5 hours	4 hours	3 hours	2 hours
Sandable	40 hours	30 hours	24 hours	20 hours
Recoatable	40 hours	30 hours	24 hours	20 hours

The above mentioned drying times are indicative at 65% RAH and 35 µm dry filmthickness. Drying also depends on ventilation and applied wet filmthickness. Higher wet filmthickness and/or poor ventilation results in longer drying times. Especially horizontal parts may take longer to dry due to high wet filmthickness. Allow each varnish coat sufficient time to dry. The additional benefit of Woodfinish Gloss is that you can overcoat the previous coat within 72 hours at 18C without the need for sanding. Still it is very much advised to lightly scratch the surface with a fine Scotch Bright.

Substrate	Bare wood : degreased and sanded P180. For maximal impregnation into the wood grain, thin first coat 25-35% .
	Maintenance of varnish: degreased and sanded P240. For a good grip, thin first coat 10% .



Epifanes Woodfinish Gloss

One-component yacht varnish alternative + extra UV filter

APPLICATION

Conditions during application Temperature **minimal 8°C. - maximal 30°C.**
 Relative air humidity **minimal 50% - maximal 85%**

Best results are achieved by longhaired soft brush or by air spray. Because of the required wet film thickness application by roller is not advised. Evenly distribute the varnish over the surface and tip off along the wood grain. Avoid retip-ping. Do not apply wet-in-wet. Do not apply excessive wet films to avoid the formation of curtains and drying problems. Avoid varnishing in direct sunlight or too much wind. A rapid loss of solvents will occur under these conditions and decrease the flowing ability. Avoid big difference in temperature of the product, surface to be varnish and working area. In case the product "pulls" and is difficult to apply, 10% thinner may be added. To retrieve the original colour of the wood, Epifanes Mahogany Stain or Epifanes Teak Stain may be added to the varnish up to 10%. After drying, lightly sand the surface with P400 or Scotch Brite. Always sand by hand along the wood grain.

Guidelines for spray application:

Thinning volume	Nozzle	Pressure	Visco DIN-cup 4 mm
15-20%	1.2 mm - 1.5 mm	2-3 Bar	20-24 sec.

SYSTEM BUILD UP

Product	Step 1	Step 2
	EPIFANES Woodfinish Gloss	EPIFANES Woodfinish Gloss
Number of coats	1	5
Thinner	EPIFANES Brushthinner PV	EPIFANES Brushthinner PV
Thinning ratio	25%	0-10%
Drying time 20°C.	24 hours	24 hours
Sanding grit	Dry P220 - sand by hand	If subsequent coat is applied within 72 hours, sanding is not needed. For smoother finish, lightly sand with P400 or Scotch Bright. After 72 hours always sand with P320-400.
Remarks	First penetrating varnish coat. For full varnish penetration into the wood fibres, apply this first coat thinned.	Do not use a heavy sanding machine. Always sand lightly by hand.

Theoretical coverage
Practicle coverage

14m² per liter @ 35 µm dry filmthickness
 Dependent on condition of substrate, loss of material due to factors such as application technique, shape of object, circumstances during application.

Recoatibility with other Epifanes varnishes

- Epifanes Clear Varnish High gloss alternative
- Epifanes Woodfinish Matte Matt finish for interior / exterior use
- Epifanes Rubbed Effect Varnish Satin finish for interior use
- Epifanes Aqua Marine Interior Varnish Water based satin finish for interior use
- Epifanes Rapidcoat / Rapidclear Semi gloss alternatief

Safety

The user of this product should obey all national laws and legislation concerning health, safety and environmental hazard. For more information on health and safety, refer to the Material Safety Data Sheet of this product.

Although the facts and suggestions in this product information sheet are based on our own research and field experiences and are believed reliable, we cannot simply be held responsible for performance or results obtained through the use of this product. Ineffectiveness or other unintended consequences may result, because of such factors as weather, conditions, presence or other materials or the manner of preparation, use or application all of which are beyond W. Heeren & Zoon's control. All such risks are assumed by user.

DISCLAIMER OF WARRANTIES. Seller makes no express warranties. THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXCLUDED. In the event a warranty is created by law, buyer's EXCLUSIVE REMEDY shall be the replacement of any defective product. No other remedy (including, but not limited to, incidental or consequential damages for lost profits, lost sales, injury to person or property, or any other incidental or consequential loss) shall be available to buyer.

W. Heeren & Zoon BV
 PO box 166
 1430 AD Aalsmeer
 Netherlands
 Phone +31 297 – 360366
 info@epifanes.nl
 www.epifanes.nl

